

VERSAFILL™

PRODUCT NAME	THICKNESS		BARRIER	OTR		WVTR		YIELD		RECOMMENDED SEAL TEMP RANGE	
	µm	mil		g /100in ²	g /100in ²	g/m ²	g /100in ²	in ² /lb	m ² /kg	°C	°F
VF221-114	114	4.5	High	< 1.0	< 0.06	< 5.0	< 0.32	6,268	8.9	130 ~ 170	266 ~ 388
VF221-140	140	5.5	High	< 1.0	< 0.06	< 4.0	< 0.26	5,104	7.2	140 ~ 180	284 ~ 356

- Precise sealing temperature depends on machine speed, dwell time and other factors. Please consult with your Flair representative for details.
- Optimized for filling temperatures up to 100C