



PRODUCT NAME	THICKNESS		BARRIER	OTR		WVTR		RECOMMENDED SEAL TEMP RANGE	
	µm	mil		cc/m ²	cc /100in ²	g/m ²	g /100in ²	°C	°F
R120-90	90	3.5	Standard	< 1,500	< 97	< 3.5	< 0.23	110 ~ 140	230 ~ 284
R120-110	110	4.3	Standard	< 1,500	< 97	< 3.0	< 0.19	110 ~ 140	230 ~ 284
R130-90	90	3.5	High	< 1.5	< 0.10	< 1.5	< 0.10	110 ~ 140	230 ~ 284
R130-110	110	4.3	High	< 1.5	< 0.10	< 1.5	< 0.10	110 ~ 140	230 ~ 284
WHITE R130-115	115	4.5	High	< 1.5	< 0.10	< 1.5	< 0.10	110 ~ 140	230 ~ 284

Precise sealing temperature depends on machine speed, dwell time and other factors. Please consult with your Flair representative for details.

